



Touch

Preliminary specification according to EN 1307

Type of manufacture	ISO 2424		Tufted 1/8 "					
Aspect	ISO 2424		Cut pile					
Dye method			Piece dyed continuous					
Width		cm	400 - 500	ft	13,1 - 16,6			
Primary backing	ISO 2424		Polypropylene woven + fleece					
Secondary backing	ISO 2424		Polypropylene woven					
Pile fibre composition	ISO 2424		Polyester					
Total thickness	ISO 1765	mm	7.8	inch	0.3			
Effective pile thickness	ISO 1766	mm	5.6	inch	0.22			
Total mass	ISO 8543	g/m²	1940	oz/yd²	57.3			
Total pile mass	ISO 2424	g/m²	1000	oz/yd²	29.5			
Effective pile mass	ISO 8543	g/m²	825	oz/yd²	24.3			
Pile density	ISO 8543	g/cm³	0.148	lb/in³	0.0053			
Number of tufts	ISO 1763	/dm²	1008	/yd²	84279			
Stroll test	ISO 6356	kV	≤ 2,0					
Vertical resistance	ISO 10965	Ohm	-					
Horizontal resistance	ISO 10965	Ohm	-					
Use classification	EN 1307		22 Domestic - moderate use					
Luxury rating	EN 1307		LC 4					
Impact sound reduction ΔL _w	ISO 10140	dB	-					
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000
		α _s	-	-	-	-	-	-
Noise reduction	ISO 354	α _w	-					
Thermal resistance	ISO 8302	m².K/W	0.108					
Flammability	EN 13501-1		Efl					
Prodis - GUT	www.pro-dis.info		49DDB8BB					



Tarkett's flooring products are to be installed in full accordance with DESSO installation instructions and recognized trade standards. An effective, regular cleaning and maintenance program is vital for retaining a high appearance level. Tarkett's flooring products should only be used as floorcoverings. Note: Tarkett reserves the right to change this specification without prior notice; changes are subject to normal production tolerances. For the latest versions of the technical specifications, visit www.tarkett.com

EN-20190516